



## Rust-Oleum® Sandable Primer - Aerosol

<b>ITEM NUMBERS</b>	#249418 Black, #249415 Gray, #249419 Red
<b>DESCRIPTION</b>	A primer that can be sanded smooth once applied to the surface.
<b>USES</b>	Ideal for bonding top coats to automotive body surfaces.
<b>APPEARANCE</b>	Available in Black, Gray and Red
<b>PACKAGING</b>	Available in 12 oz. aerosol spray can. Sandable Primer features an Any-Angle Spray system that lets you cover hard to reach places, even if the can is sprayed upside-down and also features a Comfort Tip spray nozzle to eliminate finger fatigue.
<b>SURFACE PREPARATION</b>	(See directions on can for more details)  Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces. Clean the surface with soap and water, rinse and let dry. Note: Cleaning is recommended before and after wire brushing or sanding.
<b>MIXING</b>	Shake can vigorously for one minute after mixing ball begins to rattle. Shake the can often during use.
<b>APPLICATION</b>	Use outdoors or in a well-ventilated area such as an open garage. Use when temperature is between 50°F (10°C) and 90°F (32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces that, when heated, exceed 200°F (93°C) or galvanized metal. Avoid spraying in very windy, dusty conditions. Cover surrounding area to protect from spray mist. Hold the can 12-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply 2 or more light coats a few minutes apart. When dry, the surface can be immediately recoated, top coated or wet sanded. For best results allow to dry 2-4 hours before dry sanding.

**PHYSICAL PROPERTIES** (Calculated values, may vary slightly from the actual manufactured material)

RESIN TYPE	Alkyd
SOLVENT TYPE:	Ketone/aromatic
VOC (Volatile Organic Compounds)	NA
WEIGHT PER GALLON	NA
WEIGHT PER LITER	NA
SOLIDS BY WEIGHT	27.9 – 29.4%
SOLIDS BY VOLUME	NA
RECOMMENDED DRY FILM THICKNESS PER COAT WET FILM TO ACHIEVE DFT	1.0 mil 3 mil (approximate)
PRACTICAL COVERAGE @ RECOMMENDED DFT	10 – 15 square feet
APPLICATION CONDITIONS	See above
DRY TIMES @70° - 80°F (21° - 27° C) AND 50%RH	20 minutes tack-free
SHELF LIFE	5 years

**SAFETY** (For additional information, see MSDS)

FLASHPOINT	-156F
LEAD-FREE	

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.