

VARATHANE® PREMIUM WOOD STAIN

DESCRIPTION AND USES

Varathane[®] Premium Interior Wood Stains are designed to provide deeper, richer, and more natural color for all wood projects. These stains are ideal for use on wood furniture, cabinets, doors, trim, floors, and paneling. For interior use only.

PRODUCTS			
Description	Quart	½-Pint	Gallon
Natural	211688	211755	
Summer Oak	211689	211756	237992
Golden Pecan	211710	211757	211680
Colonial Maple	211712	211759	237993
Trad'l Pecan	211713	211790	
Ipswich Pine	211714	211790	
Spring Oak	211715	211792	211994
Golden Oak	211716	211793	211681
Provincial	211717	211794	211682
Golden Mahgy.	211718	211795	237995
Light Walnut	211719	211796	237996
Light Cherry	211720	211797	237997
Chestnut	211721	211798	
Trad'l Cherry	211722	211799	211683
Red Oak	211723	211800	
Red Mahogany	211724	211801	211683
Red Chestnut	211725	211802	
Cabernet	211726	211803	223085
Amer. Walnut	211727	211804	237998
Gunstock	211728	211805	
Early American	211729	211806	211685
Dark Walnut	211730	211807	211686
Black Cherry	241411	241413	
Kona	254351	254356	
Espresso	241412	241414	
Tint Base	243857		243858

PRODUCT APPLICATION

SURFACE PREPARATION

Remove any existing finishes with sandpaper or stripper. Prepare bare wood for staining by sanding in the direction of the grain. Begin with #120 grit sandpaper and progress though #150, #180 and #220 grits.

Before staining, remove all sanding dust and dirt with a vacuum, tack cloth, or rag dampened with mineral spirits. For grease or glue, remove with a clean rag dampened with mineral spirits. Soft woods such as pine, fir, or maple require a wood conditioner. Use Varathane Premium Wood Conditioner before staining.

PRODUCT APPLICATION (cont.)

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

TESTING COLOR

Be sure to test your stain to verify the desired color. To test, apply the stain in an inconspicuous area. When testing on soft wood, be sure to sand and condition the test area. To achieve a lighter color, wipe the stain immediately after application. For a deeper color, allow the stain to set for 1 hour before wiping or apply additional coats of stain.

APPLICATION

Use only when air (ambient) temperature is between 55-90°F (13-32°C) and relative humidity is below 85%. Stir the contents thoroughly to ensure any settled pigment is re-dispersed before application. Apply with a brush or clean, lint-free cloth. Apply the stain across the grain until the wood is saturated on top. Wipe the excess stain off in the direction of the wood grain. Do not let the stain dry before wiping off the excess. A second coat can be applied after 2 hours. Do not sand between stain coats.

COVERAGE

One quart will cover up to 150 square feet. One gallon will cover up to 600 square feet. Coverage will depend on the type of wood and porosity.

DRY AND RECOAT TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 1-2 hours, dries to handle in 2 hours and can be recoated in 2 hours.

PROTECTING THE WOOD

Allow Varathane Premium Wood Stains to dry for 8 hours when applying an oil-based finish or 24 hours before applying a water-based finish.

CLEAN UP

Clean application tools and equipment with mineral spirits or paint thinner.

1 Form: GDH-363 Rev.: 022717





VARATHANE® PREMIUM WOOD STAIN

PHYSICAL PROPERTIES

		PREMIUM WOOD STAIN	
Resin Type		Urethane Modified Alkyd	
Pigment Type		Inorganic Pigments	
Solvents		Mineral Spirits	
Weight	Per Gallon	7.19-8.73 lbs.	
	Per Liter	0.86-1.04 kg	
Solids	By Weight	29.0-34.0%	
	By Volume	42.0-42.1%	
Volatile Organic Compounds		<550 g/l (4.5 lbs./gal.)	
Recommended Dry Film Thickness (DFT) Per Coat		0.5-1.0 mils (12.5-25μ)	
Wet Film to Achieve DFT (unthinned material)		1.5-3.0 mils (37.5-76µ)	
Practical Coverage at Recommended DFT (assumes 15% material loss)		125-150 sq.ft./quart 500-600 sq.ft./gal.	
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	1-2 hours	
	Handle	2 hours	
	Recoat	2 hours	
Shelf Life		3 years	
Flash Point		105°F (41°C)	
Safety Information		For additional information, see SDS	

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Phone: 877•385•8155 www.rustoleum.com

Form: GDH-363 Rev.: 022717